

POLYETHYLENE FABRICS

HT types

Style	Weight [g/m ²]	Weave	Linear density warp & weft [tex]	Setting		Thickness [mm]
				warp [threads/cm]	weft [threads/cm]	
357	35	plain	16,5	10	10	0,16
397	64	plain	22	16	11	0,20
354	130	plain	88	8	6	0,42
352	160	2/2 twill	44	18	18	0,33
359	160	2/2 twill	88	9	9	0,45
351-1	180	4HS	150	6	6	0,54

• Materials: UHMW-PE Dyneema® fibres



POLYESTER FABRICS

HT types

Style	Weight [g/m ²]	Weave	Linear density warp & weft [tex]	Setting		Thickness [mm]
				warp [threads/cm]	weft [threads/cm]	
14 K	158	plain	110	7	7	0,25
26 K	265	plain	330	3,9	3,9	0,43
Diolen-Gewebe	265	basket 2/2	110	12	11,5	0,42
25 K	520	special	330	7,8	7,8	1,14
24 K	850	special	330	12	12	1,69

